

Primer	FP400	Epoxy Primer Grey	TDS-Nr.: FP400/UK
Topcoat	TB500	PU Topcoat "Performance" High Gloss	TDS-Nr.: TB500/UK

Preparation and Pre-treatment	Characteristics
Steel, stainless steel (blasted), cast iron, galvanized steel, aluminum, glass fiber reinforced plastic. Hardened, solvent resistant surfaces, sanded original- and old paintwork. For plastic substrates – after suitability and adhesion test, use FP600 Plastic Primer.	2K Epoxy Primer
	2K PU/Acrylic Topcoat
	Total layer thickness: 100-140µm
The durability of the coating system largely depends on the thoroughness of the preparation of the surface (for more detailed information about preparing, see the Technical Information "Preparation and Pre-treatment").	Application
	Conversional spray gun,
For more Information see our Technical Information- and Data Sheets.	

Primer				
Product		Mixing ratio (Volume)	Layers	Dry times
FP400	Epoxy Primer Grey	3 parts	1-2 40-80µm	Dust dry: 20 min./20°C Recoatable: 1-48 hours/20°C Dry: 10-16 hours/20°C Force-dry: 30-40 min./60°C
AP401	Epoxy Activator	1 part		
RS405	Epoxy Reducer	+ 10-40%		
<p>For larger objects or areas with higher temperatures use RS407 Epoxy Reducer Slow.</p> <p>As Sanding Primer use 10-25% Epoxy Reducer.</p> <p>Wet on wet application use 25-40% Epoxy Reducer / 1 layer 30-40µm.</p> <p>After 48 hours please, sand again.</p> <p>FP401 Epoxy Primer DTM is the same product only the color is white.</p> <p>For higher layer thickness use Epoxy Primer FP440 Grey up to 140µm.</p>				

Topcoat				
Product		Mixing ratio (Volume)	Layers	Dry times
TB500	PU Topcoat "Performance" VOC <420g/L High Gloss	4 parts	2 45-70µm	Dust dry: 30-45 min./20°C Dry to assembly: 5-10 hours/20°C Dry: 10-16 hours/20°C Force-dry: 20-45 min./60°C
AU500	Polyurethane Activator	1 part		
RS605	Universal Reducer	+ max. 5%		

<p>For a faster process of drying use AA600 Accelerator (max.3%), to dispense with the amount of Reducer.</p> <p>Drying and curing is according to use of the wide range of Activator and Reducer.</p> <p>Possible HS Hardeners: AU577 Extra Fast, AU576 Fast, AU575 Standard and AU574 Slow (mixing ratio is the same).</p> <p>Please, see the TDS for more information.</p>

Information:
<p>If you want to weigh the components by balance, please use our VIM-CRS software.</p> <p>For airless or air mix processing, follow the instructions on our technical data sheet.</p> <p>Further Information about the products mentioned can be found in our technical data sheets.</p> <p>For recommended layer thickness, as per ISO 12944, see the information sheet TI-G9.</p>