

## GENERAL INFORMATION

1-204 MS Clear Coat is a high gloss clear finish that is very easy to use. Can be both air-dried and forced-dried.

## MIXING RATIO



2 : 1 Clear Coat : MS Hardener + 0 - 10% Uni Thinner

**If required, thin with Uni Thinner**

## GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,4	2/29
HE	1,2-1,4	1,8-2,0/26-29
Pressure tank	0,85-1,2	3,5-4,5 /51-65

## APPLICATION



2 coat 50 - 60 m (2,0-2,4 mil)

## FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F	FORCED DRY 60°C / 140°F
Flash off	5 - 10 minutes	Flash off 5 - 10 minutes
Dust free	20 - 30 minutes	Dust free -
Dry to handle	8 hours	Dry to handle 25 - 35 minutes
Dry to tape	-	Dry to tape After cooling down
Dry to sand	-	Dry to sand After cooling down
Dry to polish	8 hours	Dry to polish After cooling down

## SUBSTRATES



MM 900 - 9999 WaterBase 900+ Series and MM 500 - 5999 BeroBase 500 Series. Sanded and degreased old layers.

**Basecoat should be fully dry.**

## POT LIFE AT 20°C / 68°F



120 - 240 minutes

## INFRARED DRYING



AFTER FULL FLASH OFF AND AT PROPER DISTANCE	
Half-bake	4 min 50°C
Full-bake	10 min 65°C
See IR Manufacturer information	

## COMPONENTS



47-35 MS Hardener Fast  
 47-55 MS Hardener Medium  
 47-65 MS Hardener Slow  
 1-141 Uni Thinner Fast  
 1-151 Uni Thinner Medium  
 1-161 Uni Thinner Slow  
 47-91 Spot Repair Thinner  
 1-231 Fade-Out Thinner

## ADDITIVES



47-39 2K Elastic  
 1-060 2K Structure Coat Fine  
 1-065 2K Structure Coat Coarse

**Add before hardener.**

## SURFACE PREPARATION



**Mask entire vehicle to eliminate unwanted overspray.**



## NEXT LAYER



## PHYSICAL DATA

PHYSICAL DATA 1-204 MS CLEAR COAT		
Chemical Base	2K Polyurethane Finish	
Physical Properties	Viscosity (RT5)	17 - 18 Dincup 4 / 20°C
	Specific Gravity (kg/l)	0,981
	Flash Point Closed Cup	29°C / 84,2°F
	Volume % Solids	36,9
	Economy	7,4 m <sup>2</sup> /L/50 m 300 ft <sup>2</sup> /Gal/1,2 mil
	Gloss	High gloss
	Colour	-

## PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

[https://sds.de-beer.com/en/debeer/choose\\_localization](https://sds.de-beer.com/en/debeer/choose_localization)

## CLEAN UP



1-051 Gun Cleaner

## STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



## NOTES

**Specific information for use in Europe (EU): This product (ready for use) is not VOC compliant. Please refer to VOC declaration (2004/42/EC).**