



GENERAL INFORMATION

8-145 HS Surfacer Grey is a 2K polyurethane high filling surfacer with excellent sanding properties, which can also be used as a non-sanding surfacer. It is very easy to apply and gives high durability and appearance.

This TDS is about the Non-Sanding version.

MIXING RATIO



3 : 1 Surfacer : 2K/MS Hardener + max 20% Uni Thinner
4 : 1 Surfacer : HS Hardener + max 30% Uni Thinner
6 : 1 Surfacer : HS420 Hardener + max 35% Uni Thinner

GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,5	2/29
HE	1,3-1,5	1,8-2,0/26-29

APPLICATION



1 coat 20 - 25 µm (0,8-1,0 mil)

FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F	FORCED DRY 60°C / 140°F
Flash off	15 - 20 minutes	Flash off
Dust free	15 - 20 minutes	Dust free
Dry to handle	16 hours	Dry to handle
Dry to tape	16 hours	Dry to tape
Dry to sand	16 hours	Dry to sand
Dry to polish	-	Dry to polish



Due to small application window only for small repairs when using MM 500 - 5999 BeroBase 500 Series.

SUBSTRATES



8-145 HS Surfacer Grey should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition. (Use 1-15 Washprimer for maximum durability and rust protection.)

POT LIFE AT 20°C / 68°F



30 minutes

COMPONENTS



47-55 MS Hardener Medium
47-65 MS Hardener Slow
8-150 HS Hardener Medium
8-160 HS Hardener Slow
8-450 HS420 Hardener Medium
8-460 HS420 Hardener Slow
1-151 Uni Thinner Medium
1-161 Uni Thinner Slow
47-91 Spot Repair Thinner
1-231 Fade-Out Thinner

ADDITIVES



47-39 2K Elastic

Add before hardener.

SURFACE PREPARATION



Pre clean the surface with 1-951 Silicone Remover wipe on and wipe dry. Sand surface with P180–P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with 1-951 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



Mask entire vehicle to eliminate unwanted overspray.

NEXT LAYER



MM 900 - 9999 WaterBase 900[®] Series
MM 500 - 5999 BeroBase 500 Series
MM 2000 - 2099 BeroMix 2000 Series

Due to small application window only for small repairs when using MM 500 - 5999 BeroBase 500 Series.

PHYSICAL DATA

EU REGULATIONS		
VOC Code	2004/42/IB(c)(540)534	
Product sub category (according directive 2004/42/EC) and max VOC content (ISO 11890-1/2) of the ready to use product.	IB/c. Primer - Surfacer/filler and general (metal) primer. EU limit values: 540 g/L. (2007) This product contains a maximum of 534 g/L VOC.	
Chemical Base	2K Polyurethane Primer	
Physical Properties	Viscosity (RTS)	16 - 17 Dincup 4 / 20°C
	Specific Gravity (kg/l)	1,37
	Flash Point Closed Cup	27,5°C / 81,5°F
	Volume % Solids	41
	Economy	14 m ² /L/30 µm 570 ft ² /Gal/1,2 mil
	Gloss	Matt
	Colour	Grey



DEBEER
REFINISH

8-145
HS Surfacer Grey

PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

https://sds.de-beer.com/en/debeer/choose_localization

CLEAN UP



1-051 Gun Cleaner

STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



NOTES

-



GENERAL INFORMATION

8-145 HS Surfacers Grey Black is a 2K polyurethane high filling surfacer with excellent sanding properties, which can also be used as a non-sanding surfacer. It is very easy to apply and gives high durability and appearance.

This TDS is about the Sanding version.

MIXING RATIO



3 : 1 Surfacers : 2K/MS Hardener + max 10% Uni Thinner
4 : 1 Surfacers : HS Hardener + max 15% Uni Thinner
6 : 1 Surfacers : HS420 Hardener + max 25% Uni Thinner

GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,8	2/29
HE	1,3-1,8	1,6-1,8/23-26

APPLICATION



1-3 coat 60-180 µm (2,4-7,2 mil)

FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F		FORCED DRY 60°C / 140°F	
Flash off	5 - 10 minutes	Flash off	5 - 10 minutes	
Dust free	20 - 30 minutes	Dust free	-	
Dry to handle	16 hours	Dry to handle	20 - 30 minutes	
Dry to tape	16 hours	Dry to tape	20 - 30 minutes	
Dry to sand	16 hours	Dry to sand	20 - 30 minutes	
Dry to polish	-	Dry to polish	-	



SUBSTRATES



8-145 HS Surfacers Grey should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition. (Use 1-15 Washprimer for maximum durability and rust protection.)

POT LIFE AT 20°C / 68°F



20 - 30 minutes

COMPONENTS



47-35 MS Hardener Fast
47-55 MS Hardener Medium
47-65 MS Hardener Slow
8-130 HS Hardener Very Fast
8-140 HS Hardener Fast
8-150 HS Hardener Medium
8-160 HS Hardener Slow
8-430 HS420 Hardener Very Fast
8-440 HS420 Hardener Fast
8-450 HS420 Hardener Medium
8-460 HS420 Hardener Slow
1-141 Uni Thinner Fast
1-151 Uni Thinner Medium
1-161 Uni Thinner Slow

ADDITIVES



47-39 2K Elastic

Add before hardener.

SURFACE PREPARATION



Pre clean the surface with 1-951 Silicone Remover wipe on and wipe dry. Sand surface with P180–P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with 1-951 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



Mask entire vehicle to eliminate unwanted overspray.

NEXT LAYER



MM 900 - 9999 WaterBase 900[®] Series
MM 500 - 5999 BeroBase 500 Series
MM 2000 - 2099 BeroMix 2000 Series

PHYSICAL DATA

EU REGULATIONS	
VOC Code	2004/42/IB(c)(540)534
Product sub category (according directive 2004/42/EC) and max VOC content (ISO 11890-1/2) of the ready to use product.	11B/c. Primer - Surfacers/filter and general (metal) primer. EU limit values: 540 g/L. (2007) This product contains a maximum of 534 g/L VOC.
Chemical Base	2K Polyurethane Primer
Viscosity (RT5)	20 - 22 Dincup 4 / 20°C
Specific Gravity (kg/L)	1,41
Flash Point Closed Cup	27,5°C / 81,5°F
Volume % Solids	44
Economy	7 m ² /L/60 µm 285 ft ² /Gal/2,4 mil
Gloss	Matt
Colour	Grey



DEBEER
REFINISH

8-145
HS Surfacer Grey

PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

https://sds.de-beer.com/en/debeer/choose_localization

CLEAN UP



1-051 Gun Cleaner

STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



NOTES

-



DEBEER
REFINISH

8-14510
HS Surfacers White

GENERAL INFORMATION

8-14510 HS Surfacers White is a 2K polyurethane high filling surfacer with excellent sanding properties, which can also be used as a non-sanding surfacer. It is very easy to apply and gives high durability and appearance.

This TDS is about the Non-Sanding version.

MIXING RATIO



3 : 1 Surfacers : 2K/MS Hardener + max 20% Uni Thinner
4 : 1 Surfacers : HS Hardener + max 30% Uni Thinner
6 : 1 Surfacers : HS420 Hardener + max 35% Uni Thinner

GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,5	2/29
HE	1,3-1,5	1,8-2,0/26-29

APPLICATION



1 coat 20 - 25 µm (0,8-1,0 mil)

FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F	FORCED DRY 60°C / 140°F
Flash off	15 - 20 minutes	Flash off
Dust free	15 - 20 minutes	Dust free
Dry to handle	16 hours	Dry to handle
Dry to tape	16 hours	Dry to tape
Dry to sand	16 hours	Dry to sand
Dry to polish	-	Dry to polish

Due to small application window only for small repairs when using MM 500 - 5999 BeroBase 500 Series.

SUBSTRATES



8-14510 HS Surfacers White should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition. (Use 1-15 Washprimer for maximum durability and rust protection.)

POT LIFE AT 20°C / 68°F



30 minutes

COMPONENTS



47-55 MS Hardener Medium
47-65 MS Hardener Slow
8-150 HS Hardener Medium
8-160 HS Hardener Slow
8-450 HS420 Hardener Medium
8-460 HS420 Hardener Slow
1-151 Uni Thinner Medium
1-161 Uni Thinner Slow
47-91 Spot Repair Thinner
1-231 Fade-Out Thinner

ADDITIVES



47-39 2K Elastic

Add before hardener.

SURFACE PREPARATION



Pre clean the surface with 1-951 Silicone Remover wipe on and wipe dry. Sand surface with P180—P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with 1-951 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



Mask entire vehicle to eliminate unwanted overspray.

NEXT LAYER



MM 900 - 9999 WaterBase 900* Series
MM 500 - 5999 BeroBase 500 Series
MM 2000 - 2099 BeroMix 2000 Series

Due to small application window only for small repairs when using MM 500 - 5999 BeroBase 500 Series.

PHYSICAL DATA

EU REGULATIONS		
VOC Code	2004/42/IB(c)(540)534	
Product sub category (according directive 2004/42/EC) and max VOC content (ISO 11890-1/2) of the ready to use product.	IB/c. Primer - Surfacers/filler and general (metal) primer. EU limit values: 540 g/L. (2007) This product contains a maximum of 534 g/L VOC.	
Chemical Base	2K Polyurethane Primer	
Physical Properties	Viscosity (RTS)	16 - 17 Dincup 4 / 20°C
	Specific Gravity (kg/l)	1,38
	Flash Point Closed Cup	27,5°C / 81,5°F
	Volume % Solids	41
	Economy	13 m ² /L/30 µm 570 ft ² /Gal/1,2 mil
	Gloss	Matt
	Colour	White

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. Unless Valspar agrees otherwise in writing, Valspar makes no warranties, express or implied, and disclaims all implied warranties including warranties of merchantability or fitness for a particular use or freedom from patent infringement. Valspar will not be liable for any special, incidental or consequential damages. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. © 2012 The Valspar Corporation. All rights reserved.

Revision Date: June 2018

valspar
AUTOMOTIVE



DEBEER
REFINISH

8-14510
HS Surfacer White

PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

https://sds.de-beer.com/en/debeer/choose_localization

CLEAN UP



1-051 Gun Cleaner

STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



NOTES

-



GENERAL INFORMATION

8-14510 HS Surfacers White is a 2K polyurethane high filling surfacer with excellent sanding properties, which can also be used as a non-sanding surfacer. It is very easy to apply and gives high durability and appearance.

This TDS is about the Sanding version.

MIXING RATIO



3 : 1 Surfacers : 2K/MS Hardener + max 10% Uni Thinner
4 : 1 Surfacers : HS Hardener + max 15% Uni Thinner
6 : 1 Surfacers : HS420 Hardener + max 25% Uni Thinner

GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,8	2/29
HE	1,3-1,8	1,6-1,8/23-26

APPLICATION



1-3 coat 60 - 180 µm (2,4-7,2 mil)

FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F		FORCED DRY 60°C / 140°F	
Flash off	5 - 10 minutes	Flash off	5 - 10 minutes	
Dust free	20 - 30 minutes	Dust free	-	
Dry to handle	16 hours	Dry to handle	20 - 30 minutes	
Dry to tape	16 hours	Dry to tape	20 - 30 minutes	
Dry to sand	16 hours	Dry to sand	20 - 30 minutes	
Dry to polish	-	Dry to polish	-	



SUBSTRATES



8-14510 HS Surfacers White should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition. (Use 1-15 Washprimer for maximum durability and rust protection.)

POT LIFE AT 20°C / 68°F



20 - 30 minutes

COMPONENTS



47-35 MS Hardener Fast
47-55 MS Hardener Medium
47-65 MS Hardener Slow
8-130 HS Hardener Very Fast
8-140 HS Hardener Fast
8-150 HS Hardener Medium
8-160 HS Hardener Slow
8-430 HS420 Hardener Very Fast
8-440 HS420 Hardener Fast
8-450 HS420 Hardener Medium
8-460 HS420 Hardener Slow
1-141 Uni Thinner Fast
1-151 Uni Thinner Medium
1-161 Uni Thinner Slow

ADDITIVES



47-39 2K Elastic

Add before hardener.

SURFACE PREPARATION



Pre clean the surface with 1-951 Silicone Remover wipe on and wipe dry. Sand surface with P180–P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with 1-951 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



Mask entire vehicle to eliminate unwanted overspray.

NEXT LAYER



MM 900 - 9999 WaterBase 900[®] Series
MM 500 - 5999 BeroBase 500 Series
MM 2000 - 2099 BeroMix 2000 Series

PHYSICAL DATA

EU REGULATIONS	
VOC Code	2004/42/IB(c)(540)534
Product sub category (according directive 2004/42/EC) and max VOC content (ISO 11890-1/2) of the ready to use product.	IB/c. Primer - Surfacers/filler and general (metal) primer. EU limit values: 540 g/L. (2007) This product contains a maximum of 534 g/L VOC.
Chemical Base	2K Polyurethane Primer
Viscosity (RTS)	20 - 22 Dincup 4 / 20°C
Specific Gravity (kg/L)	1,42
Flash Point Closed Cup	27,5°C / 81,5°F
Volume % Solids	44
Physical Properties	7 m ² /L/60 µm
Economy	285 ft ² /Gal/2,4 mil
Gloss	Matt
Colour	White



DEBEER
REFINISH

8-14510
HS Surfacer White

PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

https://sds.de-beer.com/en/debeer/choose_localization

CLEAN UP



1-051 Gun Cleaner

STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



NOTES

-



GENERAL INFORMATION

8-14540 HS Surfacer Black is a 2K polyurethane high filling surfacer with excellent sanding properties, which can also be used as a non-sanding surfacer. It is very easy to apply and gives high durability and appearance.

This TDS is about the Non-Sanding version.

MIXING RATIO



3 : 1 Surfacer : 2K/MS Hardener + max 20% Uni Thinner
4 : 1 Surfacer : HS Hardener + max 30% Uni Thinner
6 : 1 Surfacer : HS420 Hardener + max 35% Uni Thinner

GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,5	2/29
HE	1,3-1,5	1,8-2,0/26-29

APPLICATION



1 coat 20 - 25 µm (0,8-1,0 mil)

FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F	FORCED DRY 60°C / 140°F
Flash off	15 - 20 minutes	Flash off
Dust free	15 - 20 minutes	Dust free
Dry to handle	16 hours	Dry to handle
Dry to tape	16 hours	Dry to tape
Dry to sand	16 hours	Dry to sand
Dry to polish	-	Dry to polish



Due to small application window only for small repairs when using MM 500 - 5999 BeroBase 500 Series.

SUBSTRATES



8-14540 HS Surfacer Black should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition. (Use 1-15 Washprimer for maximum durability and rust protection.)

POT LIFE AT 20°C / 68°F



30 minutes

COMPONENTS



47-55 MS Hardener Medium
47-65 MS Hardener Slow
8-150 HS Hardener Medium
8-160 HS Hardener Slow
8-450 HS420 Hardener Medium
8-460 HS420 Hardener Slow
1-151 Uni Thinner Medium
1-161 Uni Thinner Slow
47-91 Spot Repair Thinner
1-231 Fade-Out Thinner

ADDITIVES



47-39 2K Elastic

Add before hardener.

SURFACE PREPARATION



Pre clean the surface with 1-951 Silicone Remover wipe on and wipe dry. Sand surface with P180–P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with 1-951 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



Mask entire vehicle to eliminate unwanted overspray.

NEXT LAYER



MM 900 - 9999 WaterBase 900⁺ Series
MM 500 - 5999 BeroBase 500 Series
MM 2000 - 2099 BeroMix 2000 Series

Due to small application window only for small repairs when using MM 500 - 5999 BeroBase 500 Series.

PHYSICAL DATA

EU REGULATIONS		
VOC Code	2004/42/II(c)(540)534	
Product sub category (according directive 2004/42/EC) and max VOC content (ISO 11890-1/2) of the ready to use product.	II(B/c. Primer - Surfacer/filler and general (metal) primer. EU limit values: 540 g/L. (2007) This product contains a maximum of 534 g/L VOC.	
Chemical Base	2K Polyurethane Primer	
Physical Properties	Viscosity (RTS)	16 - 17 Dincup 4 / 20°C
	Specific Gravity (kg/l)	1,35
	Flash Point Closed Cup	27,5°C / 81,5°F
	Volume % Solids	40
	Economy	14 m ² /L/30 µm 570 ft ² /Gal/1,2 mil
	Gloss	Matt
	Colour	Black



DEBEER
REFINISH

8-14540
HS Surfacer Black

PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

https://sds.de-beer.com/en/debeer/choose_localization

CLEAN UP



1-051 Gun Cleaner

STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



NOTES

-



DEBEER
REFINISH

8-14540
HS Surfacers Black

GENERAL INFORMATION

8-14540 HS Surfacers Black is a 2K polyurethane high filling surfacer with excellent sanding properties, which can also be used as a non-sanding surfacer. It is very easy to apply and gives high durability and appearance.

This TDS is about the Sanding version.

MIXING RATIO



3 : 1 Surfacers : 2K/MS Hardener + max 10% Uni Thinner
4 : 1 Surfacers : HS Hardener + max 15% Uni Thinner
6 : 1 Surfacers : HS420 Hardener + max 25% Uni Thinner

GUN SET UP



	NOZZLE (MM)	AIR PRESSURE (BAR / PSI)
HVLP	1,3-1,8	2/29
HE	1,3-1,8	1,6-1,8/23-26

APPLICATION



1-3 coat 60 - 180 µm (2,4-7,2 mil)

FLASH OFF AND DRY TIMES



	AIR DRY 20°C / 68°F		FORCED DRY 60°C / 140°F	
Flash off	5 - 10 minutes	Flash off	5 - 10 minutes	
Dust free	20 - 30 minutes	Dust free	-	
Dry to handle	16 hours	Dry to handle	20 - 30 minutes	
Dry to tape	16 hours	Dry to tape	20 - 30 minutes	
Dry to sand	16 hours	Dry to sand	20 - 30 minutes	
Dry to polish	-	Dry to polish	-	



SUBSTRATES



8-14540 HS Surfacers Black should only be applied over well sanded/scuffed and degreased primed bare steel and primed aluminium. Well sanded GRP, polyester fillers, OEM primer and old paint systems in good condition. (Use 1-15 Washprimer for maximum durability and rust protection.)

POT LIFE AT 20°C / 68°F



20 - 30 minutes

COMPONENTS



47-35 MS Hardener Fast
47-55 MS Hardener Medium
47-65 MS Hardener Slow
8-130 HS Hardener Very Fast
8-140 HS Hardener Fast
8-150 HS Hardener Medium
8-160 HS Hardener Slow
8-430 HS420 Hardener Very Fast
8-440 HS420 Hardener Fast
8-450 HS420 Hardener Medium
8-460 HS420 Hardener Slow
1-141 Uni Thinner Fast
1-151 Uni Thinner Medium
1-161 Uni Thinner Slow

ADDITIVES



47-39 2K Elastic

Add before hardener.

SURFACE PREPARATION



Pre clean the surface with 1-951 Silicone Remover wipe on and wipe dry. Sand surface with P180-P240 grit abrasive. Remove all sanding debris with compressed air, sanding vacuum and clean with 1-951 Silicone Remover wipe on and wipe dry. Final sanding before application P280-P320 feather-edge and GRP P400.



Mask entire vehicle to eliminate unwanted overspray.

NEXT LAYER



MM 900 - 9999 WaterBase 900® Series
MM 500 - 5999 BeroBase 500 Series
MM 2000 - 2099 BeroMix 2000 Series

PHYSICAL DATA

EU REGULATIONS		
VOC Code	2004/42/IB(c)(540)534	
Product sub category (according directive 2004/42/EC) and max VOC content (ISO 11890-1/2) of the ready to use product.	IB/c. Primer - Surfacers/filler and general (metal) primer. EU limit values: 540 g/l. (2007) This product contains a maximum of 534 g/l VOC.	
Chemical Base	2K Polyurethane Primer	
Physical Properties	Viscosity (RTS)	20 - 22 Dincup 4 / 20°C
	Specific Gravity (kg/l)	1,39
	Flash Point Closed Cup	27,5°C / 81,5°F
	Volume % Solids	43
	Economy	7 m ² /L/60 µm 285 ft ² /Gal/2,4 mil
	Gloss	Matt
	Colour	Black

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. Unless Valspar agrees otherwise in writing, Valspar makes no warranties, express or implied, and disclaims all implied warranties including warranties of merchantability or fitness for a particular use or freedom from patent infringement. Valspar will not be liable for any special, incidental or consequential damages. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option. © 2012 The Valspar Corporation. All rights reserved.

Revision Date: June 2018

valspar
AUTOMOTIVE



DEBEER
REFINISH

8-14540
HS Surfacer Black

PROTECTION

Use suitable respiratory protection (*fresh air supply respirator is strongly recommended*).



For more detailed information please visit the following link for the Safety Data Sheet:

https://sds.de-beer.com/en/debeer/choose_localization

CLEAN UP



1-051 Gun Cleaner

STORAGE/SHELF LIFE

Minimum 2 years; (Under normal storage conditions 10°C - 30°C / 50°F - 90°F) (unopened container).



NOTES

-